

# All Surface Enamel

## Interior-Exterior Alkyd Primer

A11W00210 White


**SHERWIN  
WILLIAMS®**

### CHARACTERISTICS

**All Surface Enamel Primer** is designed for use on interior and exterior rusty metal surfaces.

This quality coating system provides excellent resistance to weather and sunlight. The exceptional durability allows it to be used on doors, trim, windows, and other hard wear areas, including exterior wood floors.

**Color:** White

**Coverage:** 200 sq. ft. per gallon  
@ 8 mils wet;  
3.4 mils dry

#### **Drying Time, @ 77°F, 50% RH:**

**Touch:** 30 minutes  
**Recoat:** 1 Hour  
Drying and recoat times are temperature, humidity, and film thickness dependent

**Finish:** Flat

#### **Primer White A11W00210**

(may vary by color)

#### **V.O.C. (less exempt solvents):**

497 grams per litre; 4.15 lbs. per gallon  
As per 40 CFR 59.406

**Volume Solids:** 42 ± 2%

**Weight Solids:** 63 ± 2%

**Weight per Gallon:** 11.32 lbs

**Flash Point:** 87°F PMCC

**Vehicle Type:** Alkyd

**Shelf Life:** 36 months unopened

### COMPLIANCE

As of 05/14/2020, Complies with:

<b>OTC</b>	No
<b>OTC Phase II</b>	No
<b>SCAQMD</b>	No
<b>CARB</b>	No
<b>CARB SCM 2007</b>	No
<b>Canada</b>	No
<b>LEED® v4 &amp; v4.1 Emissions</b>	No
<b>LEED® v4 &amp; v4.1 V.O.C.</b>	No
<b>EPD-NSF® Certified</b>	No
<b>MIR-Product Lens Certified</b>	No
<b>MPI®</b>	No

### APPLICATION

Apply at temperatures above 50°F,  
No reduction needed.

#### **Brush:**

Use a natural bristle brush

#### **Roller:**

Use a 1/4 to 3/8 inch lambswool cover.

For specific brushes and rollers, please refer to our Brush and Roller Guide.

#### **Spray—Airless**

Pressure 1800 p.s.i.

Tip (fine finish) .017-.019 inch

### APPLICATION TIPS

Make sure product is completely agitated (mechanically or manually) before use.

### SPECIFICATIONS

#### **Galvanized Steel Rusted**

1 coat All Surface Alkyd Enamel Primer

2 coats All Surface Alkyd Enamel

#### **Steel**

1 coat All Surface Alkyd Enamel Primer

2 coats All Surface Alkyd Enamel

# All Surface Enamel

## Interior-Exterior Alkyd Primer

### SURFACE PREPARATION

**WARNING!** Removal of old paint by sanding, scraping or other means may generate dust or fumes that contain lead. Exposure to lead dust or fumes may cause brain damage or other adverse health effects, especially in children or pregnant women. Controlling exposure to lead or other hazardous substances requires the use of proper protective equipment, such as a properly fitted respirator (NIOSH approved) and proper containment and cleanup. For more information, call the National Lead Information Center at **1-800-424-LEAD** (in US) or contact your local health authority.

Remove all surface contamination by washing with an appropriate cleaner, rinse thoroughly and allow to dry. Existing peeled or checked paint should be scraped and sanded to a sound surface. Glossy surfaces should be sanded dull. Stains from water, smoke, ink, pencil, grease, etc. should be sealed with the appropriate primer/sealer. Recognize that any surface preparation short of total removal of the old coating may compromise the service length of the system.

**Galvanized Steel Rusted:** Wash to remove any oil, grease, or other surface contamination using a water-based cleaner-degreaser. Remove all corrosion with sandpaper, steel wool, or other abrading method.

**Caulking:** Exterior gaps between windows, doors, trim, and other through-wall openings; and interior gaps between walls, ceilings, crown moldings, and other trim can be filled with the appropriate caulk after priming the surface.

**Steel:** Rust and mill scale must be removed using sandpaper, steel wool, or other abrading method. Bare steel must be primed the same day as cleaned.

### SURFACE PREPARATION

**Mildew:** Prior to attempting to remove mildew, it is always recommended to test any cleaner on a small, inconspicuous area prior to use. Bleach and bleaching type cleaners may damage or discolor existing paint films. Bleach alternative cleaning solutions may be advised.

Mildew may be removed before painting by washing with a solution of 1 part liquid bleach and 3 parts water. Apply the solution and scrub the mildewed area. Allow the solution to remain on the surface for 10 minutes. Rinse thoroughly with water and allow the surface to dry before painting. Wear protective eyewear, waterproof gloves, and protective clothing. Quickly wash off any of the mixture that comes in contact with your skin. Do not add detergents or ammonia to the bleach-water solution.

### CAUTIONS

Non-photochemically reactive.

Not for use on roofs.

Before using, carefully read **CAUTIONS on label**

**DANGER! HARMFUL OR FATAL IF SWALLOWED. COMBUSTIBLE! VAPOR HARMFUL. IRRITATES EYES, SKIN AND RESPIRATORY TRACT.** Before using, carefully read **CAUTIONS** on back panel. **CAUTIONS: ALIPHATIC HYDROCARBONS, CRYSTALLINE SILICA, XYLENE, ZINC:** Contents are **FLAMMABLE.** Vapors may cause flash fires. Keep away from heat, sparks, and open flame. During use and until all vapors are gone: Keep area ventilated - Do not smoke - Extinguish all flames, pilot lights, and heaters - Turn off stoves, electric tools and appliances, and any other sources of ignition. **VAPOR HARMFUL.** Use only with adequate ventilation. To avoid overexposure, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches, or dizziness, increase fresh air, or wear respiratory protection (NIOSH approved) or leave the area. Adequate ventilation required when sanding or abrading the dried film. If adequate ventilation cannot be provided wear an approved particulate respirator (NIOSH approved). Follow respirator manufacturer's directions for respirator use. Avoid contact with eyes and skin. Wash hands after using. Keep container closed when not in use. Do not transfer contents to other containers for storage. **FIRST AID:** In case of eye contact, flush thoroughly with large amounts of water for 15 minutes and get medical attention. For skin contact, wash thoroughly with soap and water. In case of respiratory difficulty, provide fresh air and call physician. If swallowed, call Poison Control Center, hospital emergency room, or physician immediately. **DELAYED EFFECTS FROM LONG TERM OVEREXPOSURE.** Contains solvents which can cause permanent brain and nervous system damage. Intentional misuse by deliberately concentrating and inhaling the contents can be harmful or fatal. Abrading or sanding of the dry film may release crystalline silica which has been shown to cause lung damage and cancer under long term exposure. **WARNING:** This product contains chemicals known to the State of California to cause cancer and birth defects or other reproductive harm. **DO NOT TAKE INTERNALLY. KEEP OUT OF THE REACH OF CHILDREN.**

HOTW 05/14/2020 A11W00210 29 497

### CLEANUP INFORMATION

Clean spills, spatters, and tools immediately after use with compliant cleanup solvent. Follow manufacturer's safety recommendations when using solvents.

**DANGER:** Rags, steel wool, other waste soaked with this product, and sanding residue may spontaneously catch fire if improperly discarded. Immediately place rags, steel wool, other waste soaked with this product, and sanding residue in a sealed, water-filled, metal container. Dispose of in accordance with local fire regulations.